

CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

	G-134			TYPE	P4/N	
COMPOSITION	ON					
Material	Fabric with po	lyurethane (TPU) impregnation			
■ Thickness	mm	in.				
Thickness Surface pattern Colour	Fabric					
Colour	Black					
Coefficient						
of friction	LF					
س م Material	Polyamide (PA	.)				
Plies no.						
Weft type						
Material	Fabric with po	lyurethane (TPL	J) impregnation			
	mm	in.				
Surface	Fabric					
Colour	Green					
	SPECIFICATIO	NS		_	FEATURES	
Total thickness		3.40 mm	0.13 in.		nidity influence	yes
Weight		3.70 kg/m ²	0.75 lbs./sq.ft		able to metal detector	no
Elongation at 19	6	20 N/mm	114.0 lbs./in.		nanent antistatic dynamically (UNI EN ISO 21179)	yes
Max. admissible	pull	40 N/mm	228.4 lbs./in.		ic conductivity (UNI EN ISO 284)	no
Temperature	min.	0 °C	32 °F		veying on skid bed veying on rollers	yes
resistance (1)	max.	100 °C	212 °F		veying on rollers veying on skid bed on top and return	yes yes
(1) use of the belt wit		duce its life			ighed conveying	no
Minimum roller	diameter ⁽²⁾				n neck conveying	no
■ Knife edge	_	no 200 mm	7.9 in.		ned conveying	no
Bending rollerCounter-bend		400 mm	7.9 _{In.} 15.8 in.		umulators belts	yes
			RINO joint recommend	ed Curv	ved conveyor	no
Coefficient of fri				Cher	mical resistances <u>link</u>	5
Raw steel she Laminated plant).20 [-]			COMPLIANCES	
Laminated plaSteel roller).25 [-]).20 [-]			CH EC 1907/2006 Regulation and Amendments	
Rubberized ro).20 []).30 [-]		KEA	En 20 1307/2000 Regulation and Americaniches	
		2000 mm	79 in.			
Max. production						
Max. production	OR					

Issue: 24-07-2009 Last Update: 23-06-2016

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



CONVEYOR AND PROCESS BELTS

JOINING DATA SHEET

P4-N CG-134 CODE **TYPE**

· Recommended joining procedure

SKIVED JOINT '1'



Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

Skiver	Belt thickness		Straight/	Cam/	Pulley			Top cover				
				number	wedge number T	В	Thickness adjustment	working	Т	В	Thickness adjustment	End stop switch of working
	mm	mm			mm	mm		plate	mm	mm		plate
B600 A	3,4	100	Diagonal	2-10	90	1	16,05		88	1	16,35	
B300 SA	3,4	100	Diagonal	2-10	90	1	10-15		88	1	10-10	

· Guide to the use of adhesives

Apply the K cement on the polyamide part of the splices.


Let dry for 5 minutes, then match the belt ends, paying attention to align properly.

Press according to the instructions shown.

To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

Kit: NAILCOL

· Layout of components



Press settings						
Upper platen temperature	100 °C					
Lower platen temperature	100 °C					
Curing time in press	30 min.					
Driving torque	30					

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 03-11-2006 Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.