

TYPE

CONVEYOR AND PROCESS BELTS

NA-121

CODE

Colour

Black

TECHNICAL DATA SHEET

2M12 U0-G25 GP

| COMPOSITION | | | | | | | | | |
|----------------------------------|-------------------------|---|--|--|--|--|--|--|--|
| Conveying surface | Material | Natural elastomer | | | | | | | |
| | Thickness | 2.50 mm <i>0.098 in.</i> | | | | | | | |
| | Surface pattern | GP | | | | | | | |
| | Colour | Green | | | | | | | |
| | Coefficient of friction | HF | | | | | | | |
| Textile carcass | Material | Polyester (PET) | | | | | | | |
| | Plies no. | 2 | | | | | | | |
| | Weft type | Rigid | | | | | | | |
| ing ace | Material | Fabric with polyurethane (TPU) impregnation | | | | | | | |
| | Thickness | mm <i></i> in. | | | | | | | |
| Driving surface | Surface | Fabric | | | | | | | |

| TECHNICAL SPECIFICATIONS | | | | | | |
|---|------------------------|---------|------------|-----|--|--|
| Total thickness | | 5.50 mm | 0.22 | in. | | |
| Weight | 4.50 kg/m ² | 0.92 | lbs./sq.ft | | | |
| Elongation at 1% | 12 N/mm | 69.0 | lbs./in. | | | |
| Max. admissible pull | 24 N/mm | 137.0 | lbs./in. | | | |
| Temperature resistance (1) | min. | -40 °C | -40 | °F | | |
| resistance (1) | max. | 100 °C | 212 | °F | | |
| ⁽¹⁾ use of the belt with limit values may reduce its life | | | | | | |
| Minimum roller diameter (2) | | | | | | |
| Knife edge | no | | | | | |
| Bending roller | 60 mm | 2.4 | in. | | | |
| Counter-bending | 80 mm | 3.2 | in. | | | |
| (2) The above mentioned values depend on the type of CHIORINO joint recommended | | | | | | |
| Coefficient of friction on driving surface | | | | | | |
| | | | | | | |


| Coefficient of friction on driving surface | | | | | | | |
|--|----------|--------|--|--|--|--|--|
| Raw steel sheet | 0.20 [-] | | | | | | |
| Laminated plastic/wood | 0.25 [-] | | | | | | |
| ■ Steel roller | 0.20 [-] | | | | | | |
| Rubberized roller | 0.30 [-] | | | | | | |
| Max. production width | 1800 mm | 71 in. | | | | | |

SUITABLE FOR

Wood industry

Corrugated carton: loading and conveying

Packaging Cement industry



| FEATURES | | | |
|---|-----|--|--|
| Humidity influence | no | | |
| Suitable to metal detector | no | | |
| Permanent antistatic dynamically (UNI EN ISO 21179) | yes | | |
| Static conductivity (UNI EN ISO 284) | no | | |
| Conveying on skid bed | yes | | |
| Conveying on rollers | yes | | |
| Conveying on skid bed on top and return | | | |
| Troughed conveying | no | | |
| Swan neck conveying | yes | | |
| Inclined conveying | yes | | |
| Accumulators belts | no | | |
| Curved conveyor | no | | |
| Chemical resistances <u>link</u> | 8 | | |

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Issue: 24-07-2009 Last Update: 01-03-2019

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.



CONVEYOR AND PROCESS BELTS

JOINING DATA SHEET

2M12 U0-G25 GP NA-121 CODE **TYPE**

· Recommended joining procedure

SKIVED JOINT '4'



Check our general catalogue to get further info on CHIORINO joining methods.

· Skiving instructions

| Skiver | Belt Length | | | Cam/ wedge | | | | Top cover | | | | |
|---------|-------------|----|-----------------|---------------|----|----|----------------------|-----------|----|----|----------------------|----------------------------------|
| | | | diagonal cut | number | Т | В | Thickness adjustment | working | Т | В | Thickness adjustment | End stop switch of working |
| | mm | mm | | | mm | mm | | plate | mm | mm | | plate |
| B600 A | 5,5 | 65 | Diagonal | 1.5-10 | | 0 | 18,4 | 110 | | 15 | 14,6 | 120 |
| B300 SA | | | | | | | | | | | | |

· Guide to the use of adhesives

Pour the I hardener with the R cement (pot-life 2 hours).

Apply a thin layer of above mix on both splices.


Let dry for 5 minutes, then match the belt ends, paying attention to align properly.

Press according to the instructions shown.

To ensure best joint life it is advisable not to run or tension the belt for 24 hours.

Kit: SINTECOL

· Layout of components



| Press settings | | | | | | |
|--------------------------|---------|--|--|--|--|--|
| Upper platen temperature | 100 °C | | | | | |
| Lower platen temperature | 100 °C | | | | | |
| Curing time in press | 25 min. | | | | | |
| Driving torque | 30 | | | | | |

Cooling time: it is recommended to remove the belt from the press once a temperature of 60/70 degrees C is reached.

Notes

Issue: 30-09-2005 Last Update: 30-01-2014

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.