

**TYPE** 

#### **CONVEYOR AND PROCESS BELTS**

NA-46

### **TECHNICAL DATA SHEET**

# 2M12 U0-V3 N

# COMPOSITION Material Thickness 0.30 Surface

pattern

CODE

PVC 70 Sh.A (±5)

mm 0.012 in. Smooth

Black Colour Coefficient of friction

Material Polyester (PET)

Plies no. Weft type Rigid

Material Fabric with polyurethane (TPU) impregnation

Thickness mm

Surface LdB fabric pattern Colour Grey

# **TECHNICAL SPECIFICATIONS**

Total thickness		1.90 mm	0.07	in.
Weight		2.10 kg/m <sup>2</sup>	0.43	lbs./sq.ft
Elongation at 1%		12 N/mm	69.0	lbs./in.
Max. admissible pull		24 N/mm	137.0	lbs./in.
Temperature resistance (1)	min.	-10 °C	14	°F
	max.	60 °C	140	°F
(1) Lies of the helt with limit values may reduce its life				

Use of the belt with limit values may reduce its life.

Minimum radius / diameter (2)

■ Knife edge minimum radius no

40 mm 1.57 in. ■ Bending roller min. diameter ■ Counter-bending roller min. diameter 50 mm 1.97 in.

 $^{(2)}$  The above mentioned values depend on the type of CHIORINO joint recommends

### Coefficient of friction on driving surface

Raw steel sheet 0.20 [-] ■ Laminated plastic/wood 0.25 [-] Steel roller 0.20 [-] Rubberized roller 0.30 [-]

138 in. Max. production width 3500 mm

# SUITABLE FOR

Wood: MDF particle board panels

Packaging

Supermarkets check-outs

Telescopic belts

Plastic materials moulding



#### **FEATURES**

Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	yes
Inclined conveying	no
Accumulators belts	yes
Curved conveyor	no
Chemical resistances <u>link</u>	

#### COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

**NOTES** 

Issue: 24-07-2009 Last Update: 21-12-2017

#### **DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.




#### **CONVEYOR AND PROCESS BELTS**

### **JOINING TECHNICAL DATA SHEET**

CODE NA-46 TYPE **2M12 U0-V3 N** 

# Recommended joining procedure SINGLE Z



#### Other joining methods can be used:

DIAGONAL SINGLE Z DOUBLE Z SKIVED JOINT '1'


Check our general catalogue to get further info on CHIORINO joining methods.

#### Pressing

# Heating press P\PL\PLS


Press settings			
Upper platen temperature	175 °C		
Lower platen temperature	175 °C		
Temperature gauge setting	175 °C		
Curing time in press	3 min.		
Pressure	2 bar		
Film	TC-28 - Black PVC film		
Cement			

Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



- 2. Allow the cooling cycle to be completed before removing the belt from the press.
- A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
  A periodical inspection of the thermostats is recommended, to make sure they function correctly.

# Layout of components



### Notes

Issued: 25-10-2004 Last Update: 30-01-2014

#### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.